

EXHIBIT 2

Compounds with Negligible Reactivity with OH

Non-photocurable Reactive Blend of Solvents

Zero-Volatile Organic Compound Compositions

1-Bromo propane	90% volume	Resin (106H)	Solubility
Acetone	10% volume	styrene-butadiene	S
	100 ML total	styrene	S
		styrene-isoprene-styrene	S

Adding 10% Acetone improved
the solubility of 1-bromopropane
for Alkyl, silicone, and phenolic
resin

nitrocellulose	PS
Alkyl	S
silicone	S
cellulose acetate butyrate	S
Acrylic	S

Acetone is also a non-VOC
compound.

Terpene	S
Polycarbonate	S
min ester	S

These will be useful as
coating, ink or adhesives

coumarone indane	S
PVC	S
epoxy	PS

Since some are tackifiers
which have good solvent solubility,
good adhesives will be possible
with the elastomeric resin in
combination

chlorinated rubber	S
phenolic	S
olefin	S
vinyl	S

PB